

MATERIAL AND EQUIPMENT STANDARD**FOR****GLASS - FIBER MAT (INNER WRAP)****ORIGINAL EDITION****AUG. 1993**

This standard specification is reviewed and updated by the relevant technical committee on July 1999(1) and Feb. 2013(2). The approved modifications are included in the present issue of IPS.

FOREWORD

The Iranian Petroleum Standards (IPS) reflect the views of the Iranian Ministry of Petroleum and are intended for use in the oil and gas production facilities, oil refineries, chemical and petrochemical plants, gas handling and processing installations and other such facilities.

IPS are based on internationally acceptable standards and include selections from the items stipulated in the referenced standards. They are also supplemented by additional requirements and/or modifications based on the experience acquired by the Iranian Petroleum Industry and the local market availability. The options which are not specified in the text of the standards are itemized in data sheet/s, so that, the user can select his appropriate preferences therein.

The IPS standards are therefore expected to be sufficiently flexible so that the users can adapt these standards to their requirements. However, they may not cover every requirement of each project. For such cases, an addendum to IPS Standard shall be prepared by the user which elaborates the particular requirements of the user. This addendum together with the relevant IPS shall form the job specification for the specific project or work.

The IPS is reviewed and up-dated approximately every five years. Each standards are subject to amendment or withdrawal, if required, thus the latest edition of IPS shall be applicable

The users of IPS are therefore requested to send their views and comments, including any addendum prepared for particular cases to the following address. These comments and recommendations will be reviewed by the relevant technical committee and in case of approval will be incorporated in the next revision of the standard.

Standards and Research department

No.17, Street14, North kheradmand

Karimkhan Avenue, Tehran, Iran .

Postal Code- 1585886851

Tel: 88810459-60 & 66153055

Fax: 88810462

Email: Standards@ nioc.ir

GENERAL DEFINITIONS

Throughout this Standard the following definitions shall apply.

COMPANY :

Refers to one of the related and/or affiliated companies of the Iranian Ministry of Petroleum such as National Iranian Oil Company, National Iranian Gas Company, National Petrochemical Company and National Iranian Oil Refinery And Distribution Company.

PURCHASER :

Means the "Company" where this standard is a part of direct purchaser order by the "Company", and the "Contractor" where this Standard is a part of contract document.

VENDOR AND SUPPLIER:

Refers to firm or person who will supply and/or fabricate the equipment or material.

CONTRACTOR:

Refers to the persons, firm or company whose tender has been accepted by the company.

EXECUTOR :

Executor is the party which carries out all or part of construction and/or commissioning for the project.

INSPECTOR :

The Inspector referred to in this Standard is a person/persons or a body appointed in writing by the company for the inspection of fabrication and installation work.

SHALL:

Is used where a provision is mandatory.

SHOULD:

Is used where a provision is advisory only.

WILL:

Is normally used in connection with the action by the "Company" rather than by a contractor, supplier or vendor.

MAY:

Is used where a provision is completely discretionary.

CONTENTS:

PAGE No.

1. SCOPE	4
2. REFERENCES	4
3. DEFINITIONS AND TERMINOLOGY	5
4. UNITS	5
5. DESCRIPTION	6
6. PROPERTIES	6
7. STORAGE LIFE AND PACKAGING	9
8. INSPECTION AND TESTING	9
9. LABELING	10

1. SCOPE

This Standard specification covers the minimum requirements for machine applied Glass-Fiber Mat (Inner Wrap) for reinforcement of hot bitumen and/or coal-tar enamel coatings.

Note 1:

This standard specification is reviewed and updated by the relevant technical committee on July 1999. The approved modifications by T.C. were sent to IPS users as amendment No. 1 by circular No. 101 on July 1999. These modifications are included in the present issue of IPS.

Note 2:

This standard specification is reviewed and updated by the relevant technical committee on Feb. 2013. The approved modifications by T.C. were sent to IPS users as amendment No. 2 by circular No. 377 on Feb. 2013. These modifications are included in the present issue of IPS.

2. REFERENCES

Throughout this Standard the following dated and undated standards/codes are referred to. These referenced documents shall, to the extent specified herein, form a part of this standard. For dated references, the edition cited applies. The applicability of changes in dated references that occur after the cited date shall be mutually agreed upon by the Company and the Vendor. For undated references, the latest edition of the referenced documents (including any supplements and amendments) applies.

ANSI (AMERICAN NATIONAL STANDARDS INSTITUTE)

ANSI C203 "Coal-Tar Protective Coating and Linings for Steel Water Pipelines-Enamel and Tape-Hot Applied"

ASTM (AMERICAN SOCIETY FOR TESTING AND MATERIALS)

D146 "Methods of Sampling and Testing Bitumen-Saturated Felts and Woven Fabrics for Roofing and Waterproofing" (Revision A)
D689 "Test Method for Internal Tearing Resistance of Paper" (Canceled)
D737 "Test Method for Air Permeability of Textile Fabrics"

IPS (IRANIAN PETROLEUM STANDARDS)

[IPS-E-TP-270](#) "Protective Coatings for Buried and Submerged Steel Structures"
[IPS-E-GN-100](#) "Engineering Standard for Units"

ISO (INTERNATIONAL ORGANIZATION FOR STANDARDIZATION)

ISO 5256 "Steel Pipes and Fittings for Buried or Submerged Pipelines-External and Internal Coating by Bitumen or Coal-Tar Derived Materials"
ISO 719 "Glass-Hydrolytic Resistance of Glass Grains at 98°C Method of Test and Classification"

TAPPI (US) (TECHNICAL ASSOCIATION OF THE PULP AND PAPER INDUSTRY)

TAPPI T-414 "Test for Internal Tearing Resistance of Paper"

3. DEFINITIONS AND TERMINOLOGY

For this Standard the following definitions shall apply:

BINDER

Material (s) applied to staple fibers and to strands in order to hold them in a desired arrangement.

BOROSILICATE GLASS

Any silicate glass having at least 5% of boron oxide (B_2O_3).

FILAMENT

A single textile element of a small diameter and a very long length, considered as continuous.

GLASS - FIBER MAT (MAT)

A uniform porous mat which is reinforced by strands of glass yarn to give longitudinal tensile strength.

The whole being bonded with a thermosetting resin.

PLIABILITY

The quality or state of being flexible in bending or creasing.

POROSITY

Porosity as related to air permeability is the rate of air flow through a mat under a differential pressure between the two fabric surfaces.

TENSILE STRENGTH

The maximum resistance of material to deformation in a tensile test carried to rupture;

That is, the breaking load, or force per unit cross-sectional area of the unstrained specimen.

TEAR STRENGTH

The force required either (1) to start or (2) to continue a propagate a tear in a fabric under specified condition.

THERMOSETTING RESIN

A plastic that, after having been cured by heat or other means, is substantially infusible and insoluble.

4. UNITS

This Standard is based on International System of Units (SI), as per [IPS-E-GN-100](#) except where otherwise specified.

5. DESCRIPTION

The glass-fiber mat shall be a thin, flexible, non woven uniform mat which is longitudinally reinforced across the full sheet width by continuous uniform glass filament spaced at 30 mm. max. The whole shall be bonded with a thermosetting resin.

The glass used shall be of chemically resistant borosilicate glass.

The mat shall be designed to give the degree of porosity required to ensure good "bleed through" of the enamel, during the coating process.

At the time of unrolling at ambient temperature, the successive layers of the mat shall not stick to one another.

It shall be suitable for application by line-travel equipment or in pipe mills and coating yards on fixed head coating machine.

6. PROPERTIES

The finished glass-fiber mat shall meet the requirements of Table 1 and 6.1 to 6.10 inclusive.

6.1 Appearance

The finished mat shall have a smooth surface free from visible defects such as holes, slits, folds, thin areas, leafing, frayed or uneven edges, presence of foreign bodies (oily matter, mud, etc.).

6.2 Binder

The binder shall be a thermosetting resin which can resist the action of micro-organisms and shall have a temperature resistance of 280°C (unaffected under load in hot enamel at 280°C for one minute).

The binder content shall be such that complete impregnation with the coating material is obtained during normal application.

6.3 Classification

The glass used shall be of hydrolytic class III (HGB3) as a maximum. The classification of glass as specified by ISO 719 is shown in Table 2 which is related to the consumption of acid and its equivalent of alkali [expressed as sodium oxide (Na_2O)], when tested by the method specified in that standard.

6.4 Elmendorf Tear Strength

The mat shall have an Elmendorf tear strength in the longitudinal direction of not less than 100 g and in the transverse direction of not less than 100 g by test method ASTM D689 or test method TAPPI T414.

To test, use an Elmendorf tear tester, Thwing-Albert Model 60-16 or equivalent, capacity 0-1600 g. The instrument shall be securely anchored to a table and leveled. The pendulum shall be tested for zero by moving it to the left or the pendulum stop and then released. Adjustments shall be made if the pointer does not read zero after the pendulum stop has been released. The friction of the apparatus and the condition of the knife shall be verified and adjusted, if required, as provided in ASTM D689. Make tests at a temperature of $23^\circ\text{C} \pm 2^\circ\text{C}$ and 50 ± 10 percent relative humidity. Cut 10 specimens from the mat using either a sample cutter or template notching machine direction (MD) and machine direction plus cross direction (MD plus CD). Sample size shall be $76 \text{ mm} \pm 2 \text{ mm}$ wide \times $63 \text{ mm} \pm 2 \text{ mm}$ high. The test shall initially be performed using two plies. The number of plies may subsequently have to be varied as indicated in ASTM D689. The pendulum is moved to the left until the stop is engaged. After the specimen has been clamped into the apparatus with the 63 mm slit in the vertical direction, the knife is depressed to make the slit and the stop depressed to

release the pendulum. Record the number of piles, the reading of the pointer, and whether MD or MD plus CD tear. The entire procedure is repeated to obtain 10 individual readings, and then readings are averaged. This average, divided by the number of piles tested, gives the Elmendorf tear strength.

6.5 Pliability

There shall be no cracking of glass-fiber mat when bent over a 6.4 mm. diameter mandrel at $23^{\circ}\text{C} \pm 1^{\circ}\text{C}$ for approximately 2 seconds, as determined by ASTM D146, modified. Cut five specimens, 25 mm \times 200 mm with the long dimension parallel to the length of the roll and immerse in water at $23^{\circ}\text{C} \pm 1^{\circ}\text{C}$ for 10-15 min. Remove each specimen individually and bend over a 6.4 mm diameter mandrel through a 90° arc at uniform speed in approximately 2s. Examine each specimen for cracks or breaks.

6.6 Porosity

When related to pressure difference across the sample, the glass-fiber mat shall have a porosity of not less than 0.60 mm and not more than 1.9 mm of water at an average air velocity of 60 m/min, as determined by ASTM D737, modified. Provide five specimens, at least 250 mm \times 250 mm, representative of the unsaturated glass-fiber mat to be tested, or test five places on the unsaturated glass-fiber mat as widely separated as possible without cutting. The apparatus shall consist essentially of a suction fan for drawing air through a known area of unsaturated glass-fiber mat, a circular orifice over which the mat to be tested can be clamped, a means of measuring the pressure drop across the mat, and a means of measuring the volume of air flowing through the mat. The clamp shall effectively eliminate edge leakage. The apparatus shall be capable of testing unsaturated glass-fiber mats of different thicknesses and of testing large pieces of glass-fiber mat without cutting. The instrument shall be calibrated directly with a precision instrument. Make all tests at $23^{\circ}\text{C} \pm 1^{\circ}\text{C}$ and 50 percent \pm 2 percent relative humidity. Mount the test specimen between the clamp and the circular orifice with sufficient tension to draw the unsaturated glass-fiber mat smooth. It shall not be distorted in its own plane. Draw conditioned air through the known area of the mat and through the calibrated flow meter at the rate of 60 m/min and record the pressure drop across the mat in millimeters of water. Report the average of the test results for the five test specimens or the five different locations on the glass-fiber mat as the porosity.

6.7 Thickness

The mat shall have a thickness of not less than 0.33 mm, as determined by ASTM D146, modified. At 10 equally spaced areas selected by sampling, measure the thickness with an Ames dial reading in units of 0.25 mm (ten thousandths of an inch). Use a circular foot and anvil, both 645 mm² in area, exerting a pressure of 13.8 kPa. Make all measurements in an atmosphere of 50 percent relative humidity and at $23^{\circ}\text{C} \pm 1^{\circ}\text{C}$.

6.8 Tensile Strength

In the case of reinforced glass wrap, the breaking strength in the longitudinal direction shall be no less than 118 N/50 mm width. In either case, the breaking strength in the transverse direction shall be no less than 36 N/50 mm width, as determined by ASTM D146, modified. Cut 10 specimens of 75 mm \times 560 mm with the longer dimension along the roll and 10 specimens with the longer dimension across the roll according to C203. In those instances where the wrapper width is less than 560 mm, the specimen length shall be that of the wrapper length. Impregnate both ends of each specimen with a protective coating of shellac or methacrylate for a distance of 64 mm and allow to dry. Test all specimens at $23^{\circ}\text{C} \pm 1^{\circ}\text{C}$ using a tension-testing machine of adequate capacity in which the clamps are attached to swivels that are free to move in any direction. The clamps shall be 25 mm \times 75 mm and shall be covered with masking tape. Grip the specimen 50 mm from each end, leaving 457 mm between the clamps. This gage length may have to be adjusted, depending on wrapper width. However, the length should be a maximum consistent with good clamping. Increase the breaking of the load by causing the lower clamps of the machine to travel at a uniform speed of

300 mm/min. Disregard the reading on any specimen that breaks nearer than 13 mm from either clamp and test an additional specimen in its place. Report the average of the results of 10 individual tests on specimens cut along the roll as the longitudinal breaking strength and the average of the results of 10 individual tests on specimens cut across the roll as the transverse breaking strength.

6.9 Color

The color of mat shall be light color preferably white.

6.10 Roll Sizes

The roll sizes, as specified by the purchaser, shall be as follows:

Roll length: 122 m, 244 m.

Roll Width: 102 mm, 152 mm,
229 mm, 304 mm,
457 mm.

TABLE 1- PHYSICAL CHARACTERISTICS OF GLASS-FIBER MAT

CHARACTERISTICS	UNITS	VALUES	TEST METHODS
WEIGHT (Min.)	g /m ²	41	ASTM D146
THICKNESS (Min.)	mm	0.33	ASTM D146, MODIFIED. (SEE 6.7 OF THIS STANDARD)
TENSILE STRENGTH: LONGITUDINAL (Min.)	N/50 mm WIDTH	118	ASTM D146, MODIFIED. (SEE 6.8 OF THIS STANDARD)
TRANSVERSAL (Min.)	N/50 mm WIDTH	36	
ELMENDORF TEAR STRENGTH: LONGITUDINAL (Min.)	g.	100	ASTM D689, MODIFIED. (SEE 6.4 OF THIS STANDARD)
TRANSVERSAL (Min.)	g.	100	
PLIABILITY	---	NO CRACKING	ASTM D146, MODIFIED. (SEE 6.5 OF THIS STANDARD)
POROSITY	mm of water	0.6-1.9	ASTM D737, MODIFIED. (SEE 6.6 OF THIS STANDARD)

TABLE 2 - LIMIT VALUES IN THE HYDROLYTIC RESISTANCE GRAINS TEST (BOILING WATER TEST)

CLASS ⁽¹⁾	CONSUMPTION OF HYDROCHLORIC ACID SOLUTION [c(HCl)=0.01 mol/l] PER GRAM OF GLASS GRAINS ml/g	EQUIVALENT OF ALKALI EXPRESSED AS MASS OF SODIUM OXIDE (Na ₂ O) PER GRAM OF GLASS GRAINS µg/g
HGB 1	UP TO AND INCLUDING 0,10	UP TO AND INCLUDING 31
HGB 2	From 0,10 UP TO AND INCLUDING 0,20	From 31 UP TO AND INCLUDING 62
HGB 3	From 0,20 " " " " 0,85	From 62 " " " " 264
HGB 4	From 0,85 " " " " 2,0	From 264 " " " " 620
HGB 5	From 2,0 " " " " 3,5	From 620 " " " " 1085

1) "HGB" stands for the hydrolytic resistance of glass grains according to the boiling water test method.

7. STORAGE LIFE AND PACKAGING

7.1 Storage Life

The product shall meet the requirements of clause 5, after storage for 24 months from date of delivery, in a full, tightly covered container.

7.2 Packaging

The mats purchased according to this standard shall be rolled on cardboard tubes with internal diameter of 76 mm (nominal) and packaged in suitable and approved containers so that, during stocking and transport, full quality of performance is retained.

Packing shall be weather-proof and strapped on pallets suitable for long distance shipment.

8. INSPECTION AND TESTING

8.1 All materials supplied under this standard specification shall be subject to timely inspection by the purchaser or his authorized representative.

The purchaser shall have the right to reject any material(s) supplied which is (are) found to be defective under this standard specification. In case of dispute, the arbitration, or settlement procedure, established in the procurement documents shall be followed.

8.2 Purchaser's inspector(s) shall have free access to the Supplier's works to follow up the progress of the materials covered by this standard and to check the quality of materials. The Supplier shall place free of charge at the disposal of the Purchaser's inspector (s) all means necessary for carrying out their inspection: results of tests, checking of conformity of materials with this standard requirements, checking of marking and packing and temporary acceptance of materials.

8.3 The supplier shall set up and maintain such quality assurance and inspection systems as are necessary to ensure that the materials comply in all respects with the requirements of this standard specification.

8.4 Samples submitted to the purchaser will be tested in the purchaser's laboratory or in a responsible commercial laboratory designated by the purchaser.

8.5 The supplier shall furnish the purchaser with a certified copy of results of tests made by the manufacturer covering physical and performance characteristics of each batch of material to be supplied under this standard specification.

The supplier shall furnish, or allow the purchaser to collect, samples of the material representative of each batch of mat. Certified test reports and samples furnished by the supplier shall be properly identified with each batch of material.

8.6 Prior to acceptance of the supplier's material, samples of material submitted by the supplier will be tested by the purchaser. If any sample is found not to conform to this standard, material represented by such sample will be rejected. If samples of the supplier's materials that have been previously accepted are found not to conform to this standard, all such material will be rejected.

8.7 Unless otherwise specified in this standard specification the methods of sampling and testing shall be in accordance with applicable methods of the American Society for Testing and Materials, (ASTM) and ISO 5256.

9. LABELING

9.1 Marking of Rolls

Each roll shall be clearly marked with the following:

- a) The name or trade mark of the supplier;
- b) The length of the roll (in m);
- c) The net weight of the roll (in kg);
- d) The width of the mat (in cm).
- e) Date of inspection
- f) UPC bar code part No.

9.2 Marking of Containers

Each container shall be legibly marked with the following information:

Name: GLASS - FIBER MAT (INNER WRAP)

Specification: [IPS-M-TP-300](#)

Order No.:

MESC No.:

Roll Size: LengthWidth.....

Max. Temperature resistance °C:

Batch or lot No.:

Stock No.:

Date of manufacture:

Quantity (Number of rolls):

Manufacturer's Name and Address:

Date of inspection:

Design Guide: For guidance on the usage of this material reference should be made to [IPS-E-TP-270](#).